# *Raytronics* AG

#### Wärmeschrumpftechnik

## Heat shrink tube, PEEK, high temperature

PEEK is a linear, semi-crystalline aromatic polymer and considered one of the highest performing thermoplastic materials. This tube provides all the benefits of PEEK but in a heat shrink form. PEEK heat shrinking tubes provides a layer of protection for sensitive components and critical connections. These heat shrinking tubes are best suited for applications in challenging environments such as oil and gas explorations where abrasion, intense pressure, chemicals, water or dielectric interference pose a threat to wires and electrical components. PEEK heat shrinking tubes are used for medical device protection, wire and cable encapsulation and insulation, impact and wear resistant insulation, mandrel covering and many more.

## Product Facts of heat shrink tube PEEK

- Heat shrinkable
- High continuous temperature (+260°C)
- Extends life of protected item
- Adhesion to metals
- Assures reliable performance
- Outstanding abrasion resistance

## **Temperature**

Operating temperature

+260°C

#### **Dimensions in mm**

Part Number	Sizes	Inside Diameter		Wall Thickness		
	AWG	As Supplied	After Heating	Min.	Nom.	Max.
PEEK-17-X-S	17	0.965	0.686	0.127	0.178	0.229
PEEK-16-X-S	16	1.143	0.813	0.127	0.178	0.229
PEEK-15-X-S	15	1.397	0.991	0.127	0.178	0.229
PEEK-14-X-S	14	2.159	1.524	0.127	0.178	0.229
PEEK-13-X-S	13	2.337	1.651	0.127	0.178	0.229
PEEK-12-X-S	12	2.565	1.829	0.127	0.178	0.229
PEEK-11-X-S	11	2.845	2.032	0.127	0.178	0.229
PEEK-10-X-S	10	3.175	2.261	0.127	0.178	0.229
PEEK-9-X-S	9	3.480	2.489	0.127	0.178	0.229
PEEK-8-X-S	8	4.064	2.896	0.127	0.178	0.229
PEEK-7-X-S	7	4.420	3.150	0.127	0.178	0.229
PEEK-6-X-S	6	5.080	3.632	0.127	0.178	0.229
PEEK-5-X-S	5	5.613	4.013	0.127	0.178	0.229
PEEK-4-X-S	4	6.401	4.572	0.127	0.178	0.229
PEEK-3-X-S	3	7.036	5.029	0.127	0.178	0.229
PEEK-2-X-S	2	8.026	5.740	0.127	0.178	0.229
PEEK-1-X-S	1	8.865	6.325	0.127	0.178	0.229
PEEK-0-X-S	0	9.957	7.112	0.127	0.178	0.229

#### Standard Colour

This datasheet is issued without guarantee according to the correctness of the containing information, product and service descriptions. The data has been carefully checked, Raytronics AG is not liable for any loss or damage resulting from errors or omission in hereby contained information.