

Wärmeschrumpftechnik

Moulded Parts, 301A011 to 301A048 (T-Transition)

These moulded parts or heat shrink boots are used for mechanical protection and cable strain relief. This version is ideal for cable harness applications where cable branches and breakouts are required. Our moulded parts combine an easy and quick installation with high electric strength, mechanical toughness and chemical and environmental resistance. These moulded parts are with or without coating available.





Dimensions in mm

Injection and vent port available only on request

Inside diameter (Coatir	Inside diameter (Coating reduces Ø max. 1.5mm)		R	S	W
As supplied	After heating	+/- 10%	+/- 10%	+/- 10%	+/- 30%
H, J + K	H, J + K				
6.60	3.60	30.00	15.00	15.00	1.02
13.00	6.90	59.00	30.00	30.00	1.52
26.90	13.50	120.00	60.00	60.00	2.29
55.60	30.20	246.00	123.00	123.00	3.05
	As supplied H, J + K 6.60 13.00 26.90	As supplied After heating H, J + K 6.60 13.00 26.90 After heating H, J + K 6.90 13.50	As supplied After heating +/- 10% H, J + K 6.60 3.60 30.00 13.00 6.90 59.00 26.90 13.50 120.00	As supplied After heating +/- 10% +/- 10% H, J + K H, J + K 6.60 3.60 30.00 15.00 13.00 6.90 59.00 30.00 26.90 13.50 120.00 60.00	As supplied After heating +/- 10% +/- 10% +/- 10% H, J + K H, J + K 6.60 3.60 30.00 15.00 15.00 13.00 6.90 59.00 30.00 30.00 26.90 13.50 120.00 60.00

Material (not all combinations available)

Ordering Code	Material	Operating temperature range
-3	Polyolefin, semi-rigid	-55°C to +135°C
-4	Polyolefin, flexible	-55°C to +135°C
-12	Fluoroelastomer, flexible	-55°C to +200°C
-25	Elastomer, fluid resistant	-75°C to +150°C
-100	Polyolefin, halogen free	-30°C to +105°C
-100	Polyolefin, halogen free	-30°C to +105°C

Coating, Adhesive

Ordering code	Material	Operating temperature range	
/42	Polyamide, hot-melt	-20°C to +60°C	
/86	High performance, hot-melt	-55°C to +120°C	
/225	Epoxy/Polyamide	-75°C to +150°C	

Colour